



# CF3460

**CHEMFAB® 3460** is a heavy duty **belting fabric** for use in demanding, high temperature environments where outstanding release characteristics are required. It is composed of a high quality PTFE coating on a woven glass fibre substrate. Its strength and rigidity make it ideally suited for use in large belts. CHEMFAB® 3460 is similar to CHEMFAB® 3450 except that it has a higher coated weight. Both products have a characteristic surface texture.

**CHEMFAB® 3460** is typically used in the carpet and floor covering industries, particularly where rubber or PVC backings are being processed.

TYPICAL PROPERTIES	UNIT	VALUE	TEST METHOD
<b>Weight:</b>	g/m <sup>2</sup>	1140	FTMS 191A-5041
<b>Thickness:</b>	mm	0.630	FTMS 191A-5030
<b>Tensile Strength:</b>	N/cm	740 x 840	FTMS 191A-5102
<b>Trap Tear Strength:</b>	N	200 x 250	FTMS 191A-5136
<b>PTFE Content:</b>	%	48	-
<b>Temperature Resistance:</b>	°C	-150 to +260	-
<b>Standard Widths:</b>	mm	2450	-

\*The fabrication of a conveyor belt from the above product requires the fabric to be cut and squared. This will involve a reduction in width, and thus the exact minimum width can only be confirmed on receipt of any enquiry with belt dimensions

Saint-Gobain Performance Plastics sales, fabrication and distribution facilities are situated at the following locations:

#### Ireland

Tel. +353 65 9080170  
Fax. +353 65 9080177  
E-mail: [aff.europe@saint-gobain.com](mailto:aff.europe@saint-gobain.com)

#### Germany

Tel. +49 221 9714080  
Fax. +49 221 97140835  
E-mail: [aff.germany@saint-gobain.com](mailto:aff.germany@saint-gobain.com)

#### France

Tel. +33 4 68635353  
Fax. +33 4 68632646  
E-mail: [aff.france@saint-gobain.com](mailto:aff.france@saint-gobain.com)

#### UK

Tel. +44 1706 746900  
Fax. +44 1706 746991  
E-mail: [aff.uk@saint-gobain.com](mailto:aff.uk@saint-gobain.com)

#### Spain

Tel. +34 902 300 229  
Fax. +34 902 294 429  
E-mail: [aff.spain@saint-gobain.com](mailto:aff.spain@saint-gobain.com)

[www.fff.saint-gobain.com](http://www.fff.saint-gobain.com)

CHEMFAB® is a registered trademark.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. SAINT-GOBAIN assumes no obligation or liability for any advice furnished by it or for results obtained to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. SAINT-GOBAIN warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

©2008 Saint-Gobain Performance Plastics Corporation  
KIIA-0208-014