



## CS205 A

**CHEMSTIK® 205 A** is a PTFE-coated woven fibreglass fabric with acrylic pressure sensitive adhesive on one side. The acrylic adhesive provides high initial tack, enhanced solvent resistance and is rated for service between -40°C and 177°C. A blue backing liner is applied to the adhesive surface for ease of application and for identification.

**CHEMSTIK® 205 A** is typically used in applications required good release at modest temperatures, such as in the packaging industry and for heat sealing.

TYPICAL PROPERTIES	UNIT	VALUE	TEST METHOD
<b>Base Thickness:</b>	mm	0.120	FTMS 191A-5030
<b>Adhesive Thickness:</b>	mm	0.065	FTMS 191A-5030
<b>Base PTFE-fabric Weight:</b>	g/m <sup>2</sup>	250	FTMS 191A-5041
<b>180° Peel Adhesion Strength:</b>	N/cm	4.0	ASTM D330-83
<b>Tensile Strength:</b>	N/cm	290 x 260	FTMS 191A-5102
<b>Adhesive Type:</b>	-	Acrylic	-
<b>Temperature Resistance:</b>	°C	-40 to +177	-
<b>Standard Width:</b>	mm	1000, 1010	-

\* Formerly **CHEMSTIK® 700-5 A**

Saint-Gobain Performance Plastics sales, fabrication and distribution facilities are situated at the following locations:

### Ireland

Tel. +353 65 9080170  
Fax. +353 65 9080177  
E-mail: [aff.europe@saint-gobain.com](mailto:aff.europe@saint-gobain.com)

### Germany

Tel. +49 221 9714080  
Fax. +49 221 97140835  
E-mail: [aff.germany@saint-gobain.com](mailto:aff.germany@saint-gobain.com)

### France

Tel. +33 4 68635353  
Fax. +33 4 68632646  
E-mail: [aff.france@saint-gobain.com](mailto:aff.france@saint-gobain.com)

### UK

Tel. +44 1706 746900  
Fax. +44 1706 746991  
E-mail: [aff.uk@saint-gobain.com](mailto:aff.uk@saint-gobain.com)

### Spain

Tel. +34 902 300 229  
Fax. +34 902 294 429  
E-mail: [aff.spain@saint-gobain.com](mailto:aff.spain@saint-gobain.com)

[www.fff.saint-gobain.com](http://www.fff.saint-gobain.com)

CHEMFAB® is a registered trademark.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. SAINT-GOBAIN assumes no obligation or liability for any advice furnished by it or for results obtained to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. SAINT-GOBAIN warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

©©2007 Saint-Gobain Performance Plastics Corporation  
K11R-1207-028